

**AMENDMENTS TO THE SPECIFICATION:**

Please amend the indicated paragraphs of the specification in accordance with the amendments indicated below.

Page 5, first full paragraph, amend as indicated below:

Table 1

		Comparative Example			Inventive Example			Comparative Example			Inventive Example		
		1	2	3	1	2	3	4	5	6	4	5	6
Compounding ratio (mass%)	graphite (0.5 mm $\geq$ )	25	35	35	25	35	35	10	—	—	10	—	—
	dolomite clinker (1 mm $\geq$ )	20	15	15	20	15	15	—	—	—	—	—	—
	dolomite clinker (0.2 mm $\geq$ )	35	30	30	35	30	30	35	40	40	35	40	40
	dolomite clinker (0.074 mm $\geq$ )	20	20	—	20	20	—	35	35	—	35	35	—
	magnesia clinker (0.074 mm $\geq$ )	—	—	20	—	—	20	—	—	35	—	—	35
	calcia clinker (1 mm $\geq$ )	—	—	—	—	—	—	20	25	25	20	25	25
Application of CO <sub>2</sub> treatment to clinker *1		<del>NON</del> NO	<del>NON</del> NO	<del>NON</del> NO	YES	YES	YES	<del>NON</del> NO	<del>NON</del> NO	<del>NON</del> NO	YES	YES	YES
Presence of cracks after burning process		YES	YES	YES	<del>NON</del> NO	<del>NON</del> NO	<del>NON</del> NO	YES	YES	YES	<del>NON</del> NO	<del>NON</del> NO	<del>NON</del> NO